



NIDA FLOW R P450D450
LAMINAR TRANSFER MEDIA



STYLE	P450D450		
TECHNICAL CHARACTERISTICS			
Glass composition	E-glass		
Synthetic core composition	polypropylene		ISO 4605
Weight per unit area	g/m2	1164	34,33 oz/yd2
Tolerance of the nominal value	%	+12	
Composition:			
layer 1: chopped fibers	weight	450 g/m2	13,27oz/yd2
	length	50mm/38tex	
layer 2: synthetic core	weight	250 g/m2	7,37 oz/yd2
layer 3: chopped fibers	weight	450g/m2	
	length	50mm/38tex	13,27 oz/yd2
sewing thread: PES 75D	g/m2	14	0,41oz/yd2
sewing pattern	tricot, gauge 3,5		
Cloth width(std)(1)	cm	125	DIN EN 1773
Tolerance of the nominal value	%	+2,5	
Glass type of size	suitable for UP and EP resins		
Glass coupling agent	silane		
Moisture content	%	<0,15	DIN EN ISO 3344
Tube diameter	mm	76	
SAFETY INSTRUCTION			
Toxicological behaviour	Toxicologically harmless, non-respirable		
PACKAGING			
Pallet weight	kg	300	
rolls per pallet	3X3=9		
Pallet size	115x130cm		
Packed in a cardboard box and each roll in plastic bag			
STORAGE			
In original packing. Keep dry			

Nida-Core Corp. 541 NW Interpark Place Port St. Lucie FL 34986 USA
Tel: 772.343.7300 Fax: 772.343.9700 www.nida-core.com

All tests carried out by independent laboratory. This information is provided in good faith and is subject to modifications without prior notification. It does not constitute a commitment, neither a contractual document. Nida-Core Corp will not assume any liability form use or misuse of data presented herein. Assessment of suitability is the responsibility of end user only.

Several products offered by Nida-Core Corp. are approved by:

